



12 **EUROPEAN PATENT APPLICATION**

21 Application number : **95600003.8**

51 Int. Cl.⁶ : **G01N 3/24**

22 Date of filing : **16.02.95**

30 Priority : **14.06.94 GR 94100286**

43 Date of publication of application :
20.12.95 Bulletin 95/51

84 Designated Contracting States :
DE FR GB IT NL SE

71 Applicant : **INSTITUTO MICHANIKIS YLIKON
KAI GEODOMON A.E.
Askiton 22
GR-152 36 Penteli, Athens (GR)**

72 Inventor : **Michelis, Paul
22, Askiton Str.
GR-152 36 Penteli (GR)**

54 **Specimen geometric configuration for uniform shear distribution during testing**

57 The present invention deals with the geometric configuration of a (metallic, ceramic, composite or geo-material) specimen in order to achieve uniform distribution of shear stresses-strains in a predefined region during the application of countercurrent load pairs. In addition, this invention includes the development of a specimen heating technique adapted to the proposed geometric configuration and capable of attaining high temperatures during the testing procedure. The proposed geometry is characterised by the existence of a semicircular groove that runs along the (cubic or sheet shaped) body of the specimen (drawings 1,2). An extra thin heating element (wire covered by ceramic tape) is wound along the upper and lower grooves and covered by a boron nitride layer in order to increase the temperature in the test section. Representative shear tests prove the functionality and efficiency of the proposed configuration.




Fig. 1

The present invention refers to the geometric configuration of a specimen (metallic, ceramic, composite or geo-material) that, when properly subjected to the action of pairs of loads, ensures the development of uniformly distributed shear stress-strain in the test section interior, even in the case of large material deformation. In addition, this invention refers to the development of a technique adapted to the proposed specific design, in order to heat the specimen to temperatures that may reach 1900° C during the shear tests. The major scientific and technical fields related directly with the invention include Mechanics of Materials, Technology and Strength of Metals, Alloys, Ceramics, Composites and Geo-materials and Material Testing Procedures.

Despite the fact that significant shear stresses may develop under realistic loading conditions in materials (with important effects on the design of structures), the efforts of acquiring proper design data (especially for composite materials) over the last decades have been encountered with severe difficulties concerning the determination of in-plane shear modulus and strength. The problem stems primarily from an inability to define a specimen geometry and loading configuration which will induce a state of uniform shear in the test section. Such a state is a necessary condition for the derivation of useful conclusions from the tests.

Indeed, there exists presently no generally accepted experimental technique for the measurement of in-plane shear response of materials and particularly sheet shaped materials. While many different test methods are currently available (e.g. off-axis tension test, Iosipescu shear test, Arcan shear test, rail-shear test etc.), the results obtained from these tests have often proved inconsistent. In addition, the volume of the specimen undergoing uniform shear is very limited and, therefore, the measured strength may not be representative of the material. Depending on the particular testing procedure, the variations in the reported values can be attributed to the state of shear stress in the test sections of the specimens, which is neither pure nor in most cases uniform.

Referring to the two most common shear test methods for composites, i.e. the off-axis tension test and the Iosipescu shear test, previous studies have shown that consistent results can be obtained only on the basis of proper interpretation and after corrections that take into account the non-uniform test section stress distribution. In the case of the off-axis tension test, the end-constraint effect introduces an additional shear stress component at the clamped edge of the test coupon that must be included with the applied longitudinal stress in the transformation to the principal material coordinate system. When the Iosipescu shear specimen is considered, on the other hand, correction factors have been computed using finite element simulations for the nonuniform shear-

stress distribution.

The situation worsens in the case of large specimen deformation under the shear loading. Furthermore, the modern technological needs for high temperature testing add to the difficulties encountered, as the demand for uniform temperature distribution in the test section must be taken into account.

The invention deals with the development of a specific geometric configuration of the specimen and a corresponding heating technique such that the above requirements are met. Specifically, following the examination of several geometries, the configuration shown in drawing 1 has been selected. The test section of interest, where the developing pure shear stresses are uniformly distributed, consists of a zone along the centerline of the specimen characterized by the semicircular groove on its surface. The shear stress is easily calculated from the applied boundary forces (without recourse to constitutive equations), assuming only specimen equilibrium (Drawing 1): T_{xy}

$$= \frac{L_1 \cdot \sigma_a - L_2 \cdot \sigma_b}{AB}$$

This specific geometrical shape has been selected among others (elliptical etc.) after detailed 3-D finite element simulations of the stress field on suitable grids for cubic (Drawing 2) and sheet shaped (Drawing 3) specimens.

The same computational study revealed the optimal size and location of the regions on the specimens upper and lower boundaries where loading should be applied in order to achieve uniform shear conditions at the test section. Four pairs of parallel strip loads are applied in a way such that a uniform shear field is generated in the central region (Drawing 1: Y1 Y2 Y3 Y4). The distribution of the shear stress T_{xy} is depicted in Drawing 4, while Drawing 5 shows the distribution of T_{xy} , σ_x , σ_y from the specimen centre on the x, y plane. The sheet-shaped specimen, (usual case for composites) has dimensions typically of the order of 50x50x7 mm³. In the case of cubic specimen, the size may reach 20 cm. This is a significant feature for geo-materials because it allows taking into account the tectonic discontinuities of the material during mechanical testing. It is furthermore possible to study the behaviour of cubic concrete specimens with small dimensions of aggregates.

Turning to the heating aspects, the proposed technique involves the use of an extra thin wire (resistance) that is carefully wound along the upper and lower grooves of the cubic or sheet shaped specimen. The heating element is a Cr-Ni wire 0.3 mm in diameter, which is covered by ceramic tape for better electrical insulation. The ceramic tape has been immersed in boron nitride to improve its thermal conductivity. The overall system (wire, ceramic tape) is finally covered by a boron nitride layer for better insulation from the ambient and more efficient fixing during temperature variation and load application.

The attained temperature uniformity depends essentially on the overall loading system design as this imposes the relevant boundary conditions. To avoid undesired overheating, cooling (by air or water circulation) should be applied on the loading system.

The experiments done to verify the functionality and durability of the heating system and the insulators and to measure the uniformity of temperature, took place by letting the system to reach steady state at temperatures of the order of 400°C and 800 °C for several hours. No particular operational problems were observed with the required power, while the temperature variation in the test section was of the order of 1%.

The specimen configuration as described above, with the loading and heating system, was used in a special device designed to apply the aforementioned pairs of loads and allowing observation of the specimen, with quite satisfactory results. More specifically, an adequately uniform distribution of shear stress-strain inside the test section was achieved, as shown by the comparison of the numerically calculated shear strain (under various stress states at twelve points near the centre of the specimen) with the measured strain using an optical system (drawing 6) and the recordings of a three-gage 45-deg rosette. All these independent methods resulted in good agreement of the data.

To summarise, the new geometric configuration of the specimen (cubic or sheet shaped) generates a three dimensional region (with a width of at least 5 mm) characterised by uniformly distributed shear stresses, a feature that improves the current state-of-the-art. The latter exhibits uniformity of stresses that is restricted to a two-dimensional zone of the material.

Claims

1) Method of geometrically configuring a cubic or sheet shaped (metallic, ceramic, composite or geo-material) specimen, in order to achieve uniform shear stress-strain fields in its interior when subjected to shear loading, characterised by the presence of a semicircular groove that extends along the specimen body. In the case of sheet shaped specimen the groove runs along both sides, while for a cubic specimen the grooves are opened on two opposite sites and are much deeper, in a way that the region of material left between them is only a few millimeters thick. This geometry defines the manner of applying counter-current pairs of loads on numerically selected zones of the specimen sides, so that a uniformly distributed shear stress/strain field is attained in the region between the grooves.

2) The method of claim 1 further comprising the step of heating the specially configured specimen by

winding a thin heating wire, covered by ceramic tape, along the grooves of the specimen. The wire is covered further by a boron nitride layer for better insulation, fixation and contact with the specimen body.




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5






Fig. 6



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 687 899 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
21.02.1996 Bulletin 1996/08

(51) Int Cl.⁶: G01N 3/24

(43) Date of publication A2:
20.12.1995 Bulletin 1995/51

(21) Application number: 95600003.8

(22) Date of filing: 16.02.1995

(84) Designated Contracting States:
DE FR GB IT NL SE

(30) Priority: 14.06.1994 GR 94100286

(71) Applicant:
INSTITUTO MICHANIKIS YLIKON KAI
GEODOMON A.E.
GR-152 36 Penteli, Athens (GR)

(72) Inventor: Michelis, Paul
GR-152 36 Penteli (GR)

(54) Specimen geometric configuration for uniform shear distribution during testing

(57) The present invention deals with the geometric configuration of a (metallic, ceramic, composite or geo-material) specimen in order to achieve uniform distribution of shear stresses-strains in a predefined region during the application of countercurrent load pairs. In addition, this invention includes the development of a specimen heating technique adapted to the proposed geometric configuration and capable of attaining high temperatures during the testing procedure. The proposed geometry is characterised by the existence of a semicircular groove that runs along the (cubic or sheet shaped) body of the specimen (drawings 1,2). An extra thin heating element (wire covered by ceramic tape) is wound along the upper and lower grooves and covered by a boron nitride layer in order to increase the temperature in the test section. Representative shear tests prove the functionality and efficiency of the proposed configuration.




Fig. 1

EP 0 687 899 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 95 60 0003

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	<p>DATABASE WPI Section EI, Week 8742 Derwent Publications Ltd., London, GB; Class S03, AN 87-297758 & SU-A-1 298 598 (GOSSTROI BUILDING) , 23 March 1987 * abstract *</p> <p>---</p>	1	G01N3/24
A	<p>CH-A-486 020 (IOSIPESCU) 15 February 1970 * column 4, line 29 - line 36 * * column 5, line 11 - line 40 *</p> <p>---</p>	1	<p>TECHNICAL FIELDS SEARCHED (Int.Cl.6)</p> <p>G01N</p>
A	<p>COMPOSITES, July 1980 pages 149-154, HERAKOVICH 'finite element stress analysis of a notched coupon specimen for in plane shear behaviour of composites' * page 149, column 1 - column 2; figures *</p> <p>---</p>	1	
A	<p>EXPERIMENTAL MECHANICS, vol. 30, no. 1, June 1990 pages 184-189, DADRAS 'analytical and experimental evaluation of double notch shear specimens' * page 187, column 1, paragraph 2 - column 2, paragraph 1; figures 1-4 *</p> <p>---</p>	1	
A	<p>EP-A-0 504 012 (AEROSPATIALE) 16 September 1992 * column 3, line 23 - line 37; figures *</p> <p>---</p>	1	
A	<p>US-A-4 916 954 (BUZZARD ROBERT J) 17 April 1990 * column 2, line 29 - line 35 * * column 3, line 34 - column 4, line 15; figures 4,5 *</p> <p>---</p> <p>-/--</p>	1	
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
THE HAGUE		29 December 1995	Hocquet, A
CATEGORY OF CITED DOCUMENTS			
<p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p>		<p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>	

EPO FORM 1503 01.82 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 95 60 0003

DOCUMENTS CONSIDERED TO BE RELEVANT				
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)	
A	US-A-2 617 293 (SCHNADT) * column 4, line 16 - line 24; figure 2 *	1		
A	DATABASE WPI 17 November 1982 Derwent Publications Ltd., London, GB; AN n2063 e40 & SU-A-888 001 (MIKHAILOV) , 17 December 1981 * abstract *	1		
A	PATENT ABSTRACTS OF JAPAN vol. 009 no. 257 (P-396) ,15 October 1985 & JP-A-60 105941 (KAGAKUGIJUTSUCHO KINZOKU ZAIRYO KENKYUSHO;OTHERS: OJ) 11 June 1985, * abstract *	2		
A	FR-A-2 688 590 (ENS CACHAN) * page 4, line 9 - line 27 * * page 5, line 9 - line 15; figures 2,5 *	1		
A	DATABASE WPI Week 79 Derwent Publications Ltd., London, GB; AN g3236c29 & SU-A-700 809 (DUBROV) , 30 November 1979 * abstract *	1		TECHNICAL FIELDS SEARCHED (Int.Cl.6)
A	DATABASE WPI Section EI, Week 9137 Derwent Publications Ltd., London, GB; Class S03, AN 91-272755 & SU-A-1 619 112 (AS MET SUPERPLASTIC) , 7 January 1991 * abstract *	1		
A	EP-A-0 452 216 (CUSSAC)			
The present search report has been drawn up for all claims				
Place of search THE HAGUE		Date of completion of the search 29 December 1995	Examiner Hocquet, A	
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>				

EPO FORM 150 (11.82) (P04001)